



CALTEX

Caltex Plastics
2380 East 51st Street
Vernon, California 90058
Tel : (323) 583-4140
Fax : (323) 583-8402
www.caltexplastics.com

CALPAC 1500

Jan 2019

CALPAC 1500 is the ultimate dry packaging bag on the market. It is designed for vacuum packaging moisture sensitive products. This 7 mil thick composite material provides an extremely low MVTR and high puncture resistance.

PHYSICAL PROPERTIES (proprietary ALUMINIZED PET structure / adhesive / LDPE)

TOTAL THICKNESS	7.0 mil
MOISTURE VAPOR TRANSMISSION RATE (ASTM F-1249)	<0.006 gr./100 in ² 24 hrs.
O ₂ TRANSMISSION RATE (ASTM D-3985)	0.0005/cc/100 in ² /24 hrs.
TEAR STRENGTH (ASTM D1004-66 NOTCHED)	MD 5.8 lb. TD 7.5 lb.
TENSILE STRENGTH (ASTM D882-83, A)	1100 MD psi 1300 TD psi
BURSTING STRENGTH (FTMS 101-C, 2007 1a)	130 psi
PUNCTURE STRENGTH (FTMS 101-C, 2065.1)	> 33 lb.
HEAT SEAL STRENGTH (450°F 2.0 sec., 60 psi)	> 11 lb./in.
ELONGATION (ASTM D882-83, A)	MD 40% TD 74%
LIGHT TRANSMISSION (ASTM D1003-77)	< .01%

Caltex Plastics makes no warranty, expressed or implied, as to the suitability of these materials for any specific use. The values shown above were developed from random samples taken from production material. We believe them to be typical for the product. Actual values may vary somewhat from those depicted here. Customers should determine product suitability based upon their own internal criteria.